SURFACTANT-ENHANCED CARBON REGENERATION IN LIQUID PHASE APPLICATIONS



Ms. Supiruk Sirisithichote

A Thesis Submitted in Partial Fulfillment of the Requirements
for the Degree of Master of Science
The Petroleum and Petrochemical College
Chulalongkorn University
in Academic Partnership with
The University of Michigan, The University of Oklahoma
and Case Western Reserve University

1996
ISBN 974-633-837-4

Thesis Title:

Surfactant-Enhanced Carbon Regeneration in Liquid

Phase Applications

By:

Ms. Supiruk Sirisithichote

Program:

Petrochemical Technology

Thesis Advisors:

Professor John F. Scamehorn,

Professor Somchai Osuwan



Accepted by the Petroleum and Petrochemical College, Chulalongkorn University, in Partial Fulfillment of the Requirements for the Degree of Master of Science.

Director of the College

(Prof. Somchai Osuwan)

Thesis Committee:

(Prof. John F. Scamehorn)

(Prof. Somchai Osuwan)

(Assoc. Prof. Shooshat Baramee)

Shooshot Barame

ABSTRACT

##941017 : MAJOR PETROCHEMICAL TECHNOLOGY

KEY WORDS: SURFACTANT/ REGENERATION/ ACTIVATED

CARBON/ PHENOL/ SOLUBILIZATION/ MICELLIZATION

SUPIRUK SIRISITHICHOTE: SURFACTANT-ENHANCED CARBON

REGENERATION IN LIQUID PHASE APPLICATIONS: THESIS

ADVISORS: PROF. JOHN F. SCAMEHORN, Ph.D., PROF. SOMCHAI

OSUWAN, Ph.D., 53 pp., ISBN 974-633-837-4

Surfactant-Enhanced Carbon Regeneration (SECR) is a novel, in-situ process in which a concentrated surfactant solution is used to desorb the adsorbed solutes from the spent carbon. The concentrated surfactant which has a concentration higher than its CMC will form aggregated molecule called micelles. The solute will solubilize into the micelle. Residual adsorbed surfactant can be pulled out from carbon by a water flush. The surfactant used can be selected so that it has extremely low toxicity and is biodegradable. In this study, phenol was used as the adsorbed solute and sodium dodecyl sulfate was used as the anionic surfactant. This study demonstrates the effects of low concentration of organic solute (phenol) loading by measuring the breakthrough curves for subsequent adsorption cycles following the regeneration. At the low concentration of phenol, the adsorption was mainly affected by equilibrium limit, but when the concentration of phenol increased, the mass transfer limit tended to increase the effect on adsorption. More than 26% of adsorbed phenol was removed from the bed when applied with a moderate amount of surfactant regenerant solution.

บทคัดย่อ

สุภิรักษ์ สิริสิทธิโชติ : การใช้สารลดแรงตึงผิวเพื่อนำเอาถ่านกัมมันต์ที่อิ่มตัวด้วยสาร อินทรีย์ในวัฏภาคของเหลวกลับมาใช้ใหม่ (Surfactant - Enhanced Carbon Regeneration in Liuid Phase Applications) อ. ที่ปรึกษา : ศ. คร. จอห์น เอฟ สเกมาฮอร์น (Prof. John F. Scamehorn), ศ. คร. สมชาย โอสุวรรณ, 52 หน้า, ISBN974-633-837-4

ปัญหาที่สำคัญของการใช้ถ่านกัมมันต์ (Activated Carbon) คือการหาวิธีที่เหมาะสมใน การเอาถ่านกลับมาใช้ใหม่หลังจากอิ่มตัวด้วยสารอินทรีย์แล้ว การใช้สารลดแรงตึงผิวเพื่อนำเอา ถ่านกัมมันต์ที่อิ่มตัวด้วยสารอินทรีย์กลับมาใช้ใหม่เป็นทางเลือกใหม่ทางหนึ่ง วิธีการนี้อาศัย คุณสมบัติที่สำคัญของสารลดแรงตึงผิวในการรวมตัวในรูปของไมเซลล์(Micellization) ซึ่งจะช่วย ให้สารอินทรีย์สามารถละลายในสารลดแรงตึงผิว(Solubilization)ได้มากกว่าสารละลายในสภาวะ ปกติ

งานวิจัยนี้ศึกษาผลของความเข้มข้นของสารอินทรีย์ที่มีต่อประสิทธิภาพของวิธีการนำเอา ถ่านกัมมันต์กลับมาใช้ใหม่นี้ โดยมุ่งเน้นที่ความเข้มข้นต่ำ สารอินทรีย์ที่ใช้ในการทคลอง คือ ฟืนอล (Phenol) และสารลดแรงตึงผิวคือ โซเดียม โคเคคซิล ซัลเฟต (Sodium Dodecyl Sulfate) ที่มีใช้กันอย่างแพร่หลายในอุตสาหกรรม

จากการทดลองพบว่าที่ความเข้มข้นต่ำ การคูดซับของสารอินทรีย์บนถ่านกัมมันต์จะถูก ควบคุม โดยสมคุลของการคูดซับ แต่เมื่อความเข้มข้นเพิ่มขึ้นการถ่าย โอนมวลสารจะเข้ามามี อิทธิพลต่อการคูดซับมากขึ้น วิธีการนี้สามารถดึงเอาสารอินทรีย์ออกจากถ่านกัมมันต์ ได้มากกว่า 26% ซึ่งไม่สูงมากนักเมื่อเทียบกับงานวิจัยก่อนหน้านี้ เนื่องจากพบว่าสารลดแรงตึงผิวบางส่วนมี การตกตะกอนเกิดขึ้นจึงทำให้มีการรวมตัวเป็นไมเซลล์ ได้น้อยลง และ ยังเกิดการปกคลุมของ ตะกอน บนถ่านกัมมันต์ทำให้สารอินทรีย์ถูกคูดซับบนถ่านได้น้อยลง

อย่างไรก็ตามวิธีการนี้เป็นทางเลือกใหม่ที่น่าสนใจ ซึ่งควรจะศึกษาถึงสภาวะที่เหมาะสม ที่จะให้ได้ประสิทธิภาพในการใช้งานมากที่สุดเพื่อนำไปประยุกต์ใช้ในอุตสาหกรรมต่อไป

ACKNOWLEDGEMENTS

Special thank is due to Professor John F. Scamehorn and Professor Somchai Osuwan for giving me a chance to work on this interesting thesis and also for their assistance throughout the course of my work.

I would like to acknowledge the KAO (Thailand) Industrial Co.,Ltd. for supplying sodium dodecyl sulfate and Calgon Co.,Ltd. for providing activated carbon.

I gratefully thank the National Research Council of Thailand for financial support on my work.

I particularly wish to thank the individuals who are valuable in making my work successful: the college staff, Anawat, all of my friends, and many others whose name can not be listed here.

Sincerely thank is due to Dr. John O'Haver and his wife for their kindness all the time that I spent at the University of Oklahoma.

Finally, my greatest appreciation is reserved for my parents, who allowed me the path that I followed. Thanks for my sisters and brothers who cheer me up all the time.

TABLE OF CONTENTS

СНАРТ	CHAPTER		PAGE
	TIT	LE PAGE	i
	ABS	STRACT	iii
	ACI	KNOWLEDGEMENTS	v
	TAI	BLE OF CONTENTS	vi
	LIS	T OF TABLES	viii
	LIS	T OF FIGURES	ix
I	INT	TRODUCTION	1
п	THEORY		
	2.1	Activated carbon	4
	2.2	Adsorption of organic contaminant on activated	8
		carbon	
	2.3	Adsorption of surfactant on activated carbon	11
	2.4	Surfactant and micellization	12
	2.5	Solubilization of organic contaminants in micelle	15
	2.6	Previous works of SECR	19
ш	EXPERIMENT		
	3.1	Materials	21
	3.2	Equipment	21
	3.3	Methodology	25
IV	RES	SULTS AND DISCUSSION	28

CHAP	TER	PAGE
v	CONCLUSIONS	37
	REFERENCES	38
	APPENDIX	41

LIST OF TABLES

	PAGE
Surface areas of typically available activated carbon	4
Physical properties and specification of activated carbon	38
Physical properties of chemicals used	39
The amount of phenol in effluent of phenol	
30 mg/L loading	40
The amount of phenol in effluent of phenol	
20 mg/L loading	42
The amount of phenol in effluent of phenol	
10 mg/L loading	45
The % removal of phenol in regeneration step	48
	Physical properties and specification of activated carbon Physical properties of chemicals used The amount of phenol in effluent of phenol 30 mg/L loading The amount of phenol in effluent of phenol 20 mg/L loading The amount of phenol in effluent of phenol 10 mg/L loading

LIST OF FIGURES

FIGURE		PAGE
1.1	Process strategy for surfactant-enhanced carbon	
	regeneration.	3
2.1	Micelle orientation in aqueous phase.	14
2.2	The sites in micelle provided for solubilization.	16
2.3	Schematic in solubilization of three different solubilizates.	18
3.1	Schematic diagram of experimental apparatus.	23
4.1	The breakthrough curves of phenol loading in adsorption	
	step.	29
4.2	Comparison the breakthrough curves of this work with the	
	previous work done by Bhummasobhana et al. (In press.).	30
4.3	The effect of SDS regenerant solution on phenol removal	31
4.4	The percentage of phenol removal in regeneration step.	32
4.5	The breakthrough curves of phenol loading in subsequent	
	adsorption step.	33
4.6	The effect of SECR on the breakthrough curves of phenol	
	adsorbed in adsorption step and subsequent adsorption step	
	: 10 mg/L phenol.	34
4.7	The effect of SECR on the breakthrough curves of phenol	
	adsorbed in adsorption step and subsequent adsorption step	
	: 20 mg/L phenol.	34
4.8	The effect of SECR on the breakthrough curves of phenol	
	adsorbed in adsorption step and subsequent adsorption step	
	: 30 mg/L phenol.	35
4.9	The comparison of phenol amount concerned in each	
	step.	36