

REFERENCES

- Alessandro, T., Carla, L., Marta, B., and Giuliano, D. (1999). The utilization of ceria in industrial catalysis. Catalysis Today, 50, 353-367.
- Bekyarova, E., Fornasiero, P., Kašpar, J., and Graziani, M. (1998). CO oxidation on Pd/CeO₂-ZrO₂ catalysts. Catalysis Today, 45, 179-183.
- Cauqui, M. A. and Rodriquez-Izquierdo, J. M. (1992). Application of the sol-gel methods to catalyst preparation. Journal of Non-Crystalline Solids, 147&148, 724-738.
- Colón, G., Valdivieso, F., Pijolat, M., Baker, R. T., Calvino, J. J., and Bernal, S. (1999). Textural and phase stability of Ce_xZr_{1-x}O₂ mixed oxides under high temperature oxidising conditions. Catalysis Today, 50, 271-284.
- Daniela, T., Alessandro, T., and Jordi, L. (1998). The preparation of high surface area CeO₂-ZrO₂ mixed oxides by a surfactant-assisted approach. Catalysis Today, 43, 79-88.
- Fornasiero, P., Di Monte, R., Ranga Rao, G., Kašpar, J., Meriani, S., Trovarelli, A., and Graziani, M. (1995). Rh-loaded CeO₂-ZrO₂ solid solutions as highly efficient oxygen exchangers: dependence of the reduction behavior and the oxygen storage capacity on the structural properties. Journal of Catalysis, 151, 168-177.
- Gonzalez, R. D., Lopez, T., and Gomez, R. (1997). Sol-Gel preparation of supported metal catalysts. Catalysis Today, 35, 293-317.
- González-Velasco, J. R., Gutiérrez-Ortiz, M. A., Jean-Louis, M., Botas, J. A., González-Marcos, M. P., and Gilbert, B. (1999). Contribution of cerium/zirconium mixed oxides to the activity of a new generation of TWC. Applied Catalysis B: Environmental, 22, 167-178.

- Haruta, M. and Sano, H. (1983). Preparation of highly active composite oxide of silver for hydrogen and carbonmonoxide oxidation. Preparation of Catalysis III-Studies in Surface Science and Catalysis, Amsterdam: Elsevier.
- Kašpar, J., Fornasiero, P., and Graziani, M. (1999). Use of CeO₂-based oxides in the three-way catalysis. Catalysis Today, 50, 285-298.
- Luo, M. F. and Zheng, X M. (1999). Redox behaviour and catalytic properties of Ce_{0.5}Zr_{0.5}O₂-supported palladium catalysts. Applied Catalysis A: General, 189, 15-21.
- Meeyoo, V. and Wright, P. (1999). Preparation of mixed oxide catalysts via sol-gel technique. Submitted in Catalysis Today.
- Otsuka, K., Wang, Y., and Nakamura, M. (1999). Direct conversion of methane to synthesis gas through gas-solid reaction using CeO₂-ZrO₂ solid solution at moderate temperature. Applied Catalysis A: General, 183, 317-324.
- Ozawa, M. and Loong, C. K. (1999). In situ X-ray and neutron powder diffraction studies of redox behavior in CeO₂-containing oxide catalysts. Catalysis Today, 50, 329-342.
- Purcell, K. (1997). Chemistry and Chemical Reactivity, 2ed, New York: Academic Press.
- Putna, E. S., Bunluesin, T., and Fan, X. L. (1999). Ceria films on zirconia substrates: models for understanding oxygen-storage properties. Catalysis Today, 50, 343-352.
- Rossignol, S., Madier, Y., and Duprez, D. (1999). Preparation of zirconia - ceria materials by soft chemistry. Catalysis Today, 50, 261-270.
- Tanielyan, S. K. and Augustine, R. L. (1992). Effect of catalyst pretreatment on the oxidation of carbon monoxide over coprecipitation gold catalysts. Applied Catalysis A: General, 85, 73-87.

- Vidal, H., Bernal, S., Kašper, J., Pijolat, M., Perrichon, V., Blanco, G., Pintado, J. M., Baker, R. T., Col n, G., and Fally, F. (1999). Influence of high temperature treatments under net oxidizing and reducing conditions on the oxygen storage and buffering properties of a $\text{Ce}_{0.68}\text{Zr}_{0.32}\text{O}_2$. *Catalysis Today*, 54, 93-100.
- Vidmar, P., Fornasiero, P., Kašpar, J., Gubitosa, G., and Graziani, M. (1997). Effects of trivalent dopants on the redox properties of $\text{Ce}_{0.6}\text{Zr}_{0.4}\text{O}_2$ mixed oxide. *Journal of Catalysis*, 171, 160-168.

APPENDIX

Table A-1 Pore volume of the mixed oxide catalysts with the aging time = 50 h

Calcination Temperature (°C)	Pore Volume (cc/g)					
	Ratio of Ce : Zr					Ce : Y
	100 : 0	75 : 25	50 : 50	25 : 75	0 : 100	
Not Calcined	0.00525	0.00346	0.04017	0.05925	0.15130	0.00538
500	0.03330	0.03473	0.03144	0.02342	0.01970	0.00768
700	0.00744	0.01271	0.01005	0.00180	0.00760	-
900	0.00139	0.00177	0.00296	0.00627	0.00341	-

Table A-2 Pore volume of the mixed oxide catalysts with the aging time = 80 h

Calcination Temperature (°C)	Pore Volume (cc/g)				
	Ratio of Ce : Zr				
	100 : 0	75 : 25	50 : 50	25 : 75	0 : 100
Not Calcined	0.00507	0.00151	0.00431	0.00563	0.06605
500	0.04049	0.03689	0.04198	0.03484	0.02470
700	0.01345	0.01139	0.02195	0.01279	0.00285
900	0.00180	0.00382	0.00518	0.01204	0.01136

Table A-3 Pore volume of the mixed oxide catalysts with the aging time = 120 h

Calcination Temperature (°C)	Pore Volume (cc/g)				
	Ratio of Ce : Zr				
	100 : 0	75 : 25	50 : 50	25 : 75	0 : 100
Not Calcined	0.00917	0.02738	0.06405	0.1006	0.05869
500	0.04889	0.04983	0.04881	0.04543	0.02329
700	0.01118	0.0172	0.02329	0.02886	0.01305
900	0.00210	0.00312	0.01012	0.01217	0.00955

Table A-4 Average pore radius of the mixed oxide catalysts with the aging time = 50 h

Calcination Temperature (°C)	Average Pore Radius (Å)					
	Ratio of Ce : Zr					Ce : Y
	100 : 0	75 : 25	50 : 50	25 : 75	0 : 100	50 : 50
Not Calcined	6.300	4.9770	7.5680	5.4230	7.6560	6.4790
500	6.3760	6.8370	5.9870	5.0830	4.9850	6.480
700	2.4330	4.2080	4.1620	0.7350	4.1120	-
900	3.4170	4.0745	4.7030	5.5615	5.1250	-

Table A-5 Average pore radius of the mixed oxide catalysts with the aging time = 80 h

Calcination Temperature (°C)	Average Pore Radius (Å)				
	Ratio of Ce : Zr				
	100 : 0	75 : 25	50 : 50	25 : 75	0 : 100
Not Calcined	6.1175	4.4370	5.3330	5.0260	5.0790
500	6.6930	6.780	8.2830	7.2280	5.3990
700	5.5160	5.6430	7.2310	5.0380	5.7040
900	5.3940	5.5380	5.3520	6.2250	6.41550

Table A-6 Average pore radius of the mixed oxide catalysts with the aging time = 120 h

Calcination Temperature (C)	Average Pore Radius (Å)				
	Ratio of Ce : Zr				
	100 : 0	75 : 25	50 : 50	25 : 75	0 : 100
Not Calcined	8.335	6.386	7.55	7.752	7.9085
500	9.301	8.659	7.787	6.795	5.399
700	7.053	6.864	7.042	7.23	5.373
900	6.268	6.509	7.078	7.128	5.703

CURRICULUM VITAE

Name : Ms. Matina Thammachart

Birth Date : June 1, 1976

Nationality : Thai

University Education :

1994 – 1997 Bachelor's Degree of Chemical Technology
 Chulalongkorn University, Bangkok, Thailand