

**TS-1 CRYSTALLIZATION SYNTHESIS UNDER MICROWAVE  
HYDROTHERMAL CONDITIONS**

Ms. Methira Krissanasaeranee

A Thesis Submitted in Partial Fulfilment of the Requirements  
for the Degree of Master of Science  
The Petroleum and Petrochemical College, Chulalongkorn University  
in Academic Partnership with  
Case Western Reserve University, The University of Michigan,  
The University of Oklahoma, and Institut Français du Pétrole

2004

ISBN 974-9651-57-X

*I 21616061*

**Thesis Title:** TS-1 Crystallization Synthesis Under Microwave  
Hydrothermal Conditions  
**By:** Ms. Methira Krissanasaeranee  
**Program:** Polymer Science  
**Thesis Advisors:** Assoc. Prof. Sujitra Wongkasemjit  
Prof. Erdogan Gulari  
Prof. Alexander M. Jamieson

---

Accepted by the Petroleum and Petrochemical College, Chulalongkorn  
University, in partial fulfilment of the requirements for the Degree of Master of  
Science.

*K. Bunyakit.*

..... College Director  
(Assoc. Prof. Kunchana Bunyakit)

**Thesis Committee:**

*Sujitra Wongkasemjit*  
.....  
(Assoc. Prof. Sujitra Wongkasemjit)

*Erdogan Gulari*  
.....  
(Prof. Erdogan Gulari)

*Alexander M. Jamieson*  
.....  
(Prof. Alexander M. Jamieson)

*Somchai Osuwan*  
.....  
(Prof. Somchai Osuwan)

*Anuvat Sirivat*  
.....  
(Assoc. Prof. Anuvat Sirivat)

## ABSTRACT

4572011063: POLYMER SCIENCE

Methira Krissanasaeranee: TS-1 Crystallization Synthesis Under  
Microwave Hydrothermal Conditions

Thesis Advisors: Assoc. Prof. Sujitra Wongkasemjit, Prof. Erdogan  
Gulari and Prof. Alexander M. Jamieson, 37 pp. ISBN 974-9651-  
57-X

Keywords: TS-1 Zeolite / Silatrane / Titanium glycolate / OOPS  
method and Microwave technique

TS-1 zeolite has been known for its high efficiency and molecular selectivity in oxidation with  $H_2O_2$  under mild conditions. The influences of various synthesis parameters such as the mole ratios of Si/Ti, NaOH/Si, TPA/Si,  $H_2O$ /Si, the reaction time, the reaction temperature, and the aging time on the crystallization of TS-1 zeolite were investigated using the microwave technique. The moisture-stable and inexpensive titanium glycolate and silatrane, synthesized by the Oxide One Pot Synthesis (OOPS) method, were used as the precursors. The crystalline products were characterized using XRD, SEM, DR-UV, and FTIR. The DR-UV result indicates that the percentage of Ti loading into the TS-1 zeolite can be as high as 19%. An increase in the aging time decreases the crystal size, whereas an increase in the reaction time produces more uniform crystals. The optimal conditions for our crystal synthesized are: the molar ratios of  $SiO_2$ :  $0.19TiO_2$ :  $0.4NaOH$ :  $0.3TPA$ :  $114H_2O$ ; 110 hr for the aging time; 35 hr for the reaction time; and  $150^\circ C$  for the reaction temperature.

## บทคัดย่อ

เมธิรา กฤษณะเศรษฐี: การเกิดผลึกซีโอไลต์ที่เอส-วันซึ่งถูกสังเคราะห์ขึ้นภายใต้สภาวะการให้ความร้อนด้วยคลื่นไมโครเวฟ (TS-1 Crystallization Synthesis Under Microwave Hydrothermal Conditions) อ. ที่ปรึกษา: ร.ศ. ดร. สุจิตรา วงศ์เกษมจิตต์ ศ. ดร. เออร์โดแกน กุลาริ และ ศ. ดร. อเล็กซานเดอร์ เอ็ม เจมิสัน 37 หน้า ISBN 974-9651-57-X

ซีโอไลต์ที่เอส-วันเป็นที่รู้จักกันดี ในด้านการเป็น โมเลกุลที่มีความจำเพาะและมีประสิทธิภาพสูง ในการทำปฏิกิริยาออกซิเดชันกับไฮโดรเจนเปอร์ออกไซด์ภายใต้สภาวะที่ไม่รุนแรง อิทธิพลของการเปลี่ยนแปลงตัวแปรที่ใช้ในการสังเคราะห์ได้แก่ อัตราส่วนระหว่างซิลิกอนต่อไททานเนียม โซเดียมไฮดรอกไซด์ต่อซิลิกอน ทีพีเอต่อซิลิกอน น้ำต่อซิลิกอน เวลาที่ใช้ในการทำปฏิกิริยา อุณหภูมิที่ใช้ในการทำปฏิกิริยาและเวลาที่ใช้ในการเองต่อการเกิดผลึกของทีเอส-วัน ได้ถูกนำมาศึกษาวิจัยโดยใช้เทคนิคคลื่นไมโครเวฟ ไททานเนียมไกลโคเลตและโซลาเทรน เป็นสารตั้งต้นที่เสถียรต่อความชื้นและมีราคาถูก ถูกสังเคราะห์โดยใช้ปฏิกิริยาขั้นตอนเดียวที่เรียกว่า Oxide One Pot Synthesis (OOPS) ได้นำผลิตภัณฑ์ที่สังเคราะห์ไปตรวจสอบและวิเคราะห์โครงสร้างด้วยเครื่อง XRD SEM DR-UV และ FTIR ผลการวิเคราะห์จาก DR-UV ซึ่ให้เห็นว่าปริมาณร้อยละของไททานเนียมที่สามารถบรรจุลงในซีโอไลต์ที่เอส-วันนั้น สูงถึงร้อยละ 19 การเพิ่มขึ้นของเวลาที่ใช้ในการเองส่งผลทำให้ขนาดของผลึกซีโอไลต์มีความใกล้เคียงกันมากขึ้น สภาวะที่เหมาะสมที่สุดสำหรับการสังเคราะห์ผลึกซีโอไลต์ที่เอส-วัน คือ อัตราส่วนโดยโมลซิลิกอนไดออกไซด์: 0.19 ไททานเนียมไดออกไซด์: 0.4 โซเดียมไฮดรอกไซด์: 0.3 ทีพีเอ: 114 น้ำ โดยใช้เวลาในการเอง 110 ชั่วโมง เวลาในการทำปฏิกิริยา 35 ชั่วโมง และอุณหภูมิที่ใช้ในการทำปฏิกิริยา 150 องศาเซลเซียส

## ACKNOWLEDGEMENTS

This thesis could not have been achieved without my Thai Advisor, Assoc. Prof. Sujitra Wongkasemjit, who gave intensive suggestions, useful guidance, laboratory skills, constant encouragement, and vital helps throughout this research work. I also would like to give a great appreciation to my U.S. advisors, Professor Erdogan Gulari and Professor Alexander M. Jamieson for providing useful recommendations and creative comments throughout the course of her work.

I would like to extend my thanks to Ms. Noppawan Phonthammachai and Mr. Phairat Phairiyawirut for intensive guidance and suggestion throughout this work.

Finally, the author would like to take this opportunity to thank all PPC friends for their friendly assistance, cheerfulness, creative suggestions, and encouragement. The author had the most enjoyable time working with all of them. Also, the author is greatly indebted to my parents and my family for their support, love and understanding.

This thesis work is partially funded by Postgraduate Education and Research Programs in Petroleum and Petrochemical Technology (PPT Consortium).

## TABLE OF CONTENTS

	<b>PAGE</b>
Title Page	i
Abstract (in English)	iii
Abstract (in Thai)	iv
Acknowledgements	v
Table of Contents	vi
List of Tables	ix
List of Figures	x

  

<b>CHAPTER</b>		<b>PAGE</b>
<b>I</b>	<b>INTRODUCTION</b>	1
	1.1 Background	1
	1.2 Zeolite Synthesis	2
	1.3 Objective	4
<b>II</b>	<b>LITERATURE REVIEW</b>	5
	2.1 Synthesis of TS-1 Zeolite	5
<b>III</b>	<b>EXPERIMENTAL</b>	9
	3.1 Materials	9
	3.2 Experimental Equipment	9
	3.2.1 Fourier Transform Infrared Spectroscopy (FT-IR)	9
	3.2.2 Thermal Gravimetric Analysis (TGA)	10
	3.2.3 FAB <sup>+</sup> -Mass Spectroscopy (FAB <sup>+</sup> -MS)	10
	3.2.4 Scanning Electron Microscopy (SEM)	10
	3.2.5 X-Ray Diffraction (XRD)	10
	3.2.6 UV-Vis Diffuse Reflectance Spectroscopy (DR-UV)	11
	3.2.7 Microwave	11

<b>CHAPTER</b>	<b>PAGE</b>
3.3 Methodology	11
3.3.1 Silatrane Synthesis	11
3.3.2 Titanium Glycolate Synthesis	12
3.3.3 TS-1 Synthesis	12
3.3.4 Characterization	12
3.3.4.1 Characterization of titanium glycolate and silatrane precursors	12
3.3.4.2 Characterization of TS-1 zeolite	12
<b>IV RESULTS AND DISCUSSION</b>	<b>13</b>
4.1 Synthesis of Glycolato Titanium Precursor	13
4.1.1 Characterization of Titanium Glycolate Precursor	13
4.1.1.1 Thermal gravimetric analysis (TGA)	13
4.1.1.2 FAB <sup>+</sup> -mass spectroscopy (FAB <sup>+</sup> -MS)	14
4.1.1.3 Fourier transform infrared spectroscopy (FT-IR)	15
4.2 Synthesis of Silatrane Precursor	16
4.2.1 Characterization of Silatrane Precursor	17
4.2.1.1 Fourier transform infrared spectroscopy (FT-IR)	17
4.2.1.2 Thermal gravimetric analysis (TGA)	18
4.2.1.3 FAB <sup>+</sup> -mass spectroscopy (FAB <sup>+</sup> -MS)	18
4.3 Synthesis of TS-1 zeolite	19
4.3.1 Effect of Aging and Reaction Times	19
4.3.2 Effect of Temperature	22
4.3.3 Effect of Hydroxide Ion	24
4.3.4 Effect of Template	26
4.3.5 Effect of Dilution	27
4.3.6 Effect of Si/Ti Ratio	30

<b>CHAPTER</b>	<b>PAGE</b>
<b>V CONCLUSIONS</b>	<b>34</b>
<b>REFERENCES</b>	<b>35</b>
<b>CURRICULUM VITAE</b>	<b>37</b>

**LIST OF TABLES**

<b>TABLE</b>		<b>PAGE</b>
4.1	The proposed structure and the pattern of fragmentation of glycolato titanium	15
4.2	Assignment of IR spectrum of glycolato titanium	16
4.3	IR spectrum of silatrane	17
4.4	The proposed structure and the pattern of fragmentation of silatrane	19

## LIST OF FIGURES

FIGURE	PAGE
2.1 Schematic representation of the most relevant oxidation reaction catalyzed by TS-1	5
4.1 TGA profile of glycolato titanium	14
4.2 IR spectrum of glycolato titanium	16
4.3 TGA profile of silatrane	18
4.4 Effect of reaction time on TS-1 morphology after 110 hr aging time at 150°C for reaction heating time of: a) 5; b) 10; c) 15 and d) 20 hr	20
4.5 Effect of aging time on TS-1 morphology of product formed after heating for 15 hr at 150°C: a) 20; b) 60; c) 70; d) 90; e) 110; f) 130; g) 150 and h) 170 hr	21
4.6 Effect of aging time on x-ray diffractograms of product formed after heating for 15 hr at 150°C: a) 20; b) 60; c) 70; d) 90; e) 110; f) 130; g) 150 and h) 170 hr	22
4.7 Effect of reaction temperature on product morphology formed after 110 hr aging time for the reaction time of: a) 120°; b) 150° and c) 180°C	23
4.8 Effect of hydroxide concentration on products formed after aging for 110 hr and reaction temperature and time of 150°C and 15 hr, respectively, using NaOH ratio, x, of: a) 0.1; b) 0.3; c) 0.4; d) 0.5; e) 0.7 and f) 1.0	25
4.9 XRD patterns of products formed from reaction of SiO <sub>2</sub> : 0.01TiO <sub>2</sub> : 0.1 TPA: x NaOH: 114 H <sub>2</sub> O (x = 0.1, 0.3, 0.5, 0.7 and 1.0 ) with reaction conditions of 110 and 15 hr aging and reaction time, respectively, 150°C reaction temperature	26
4.10 Effect of TPA concentration on products formed from SiO <sub>2</sub> : 0.01TiO <sub>2</sub> : xTPA: 0.4 NaOH: 114 H <sub>2</sub> O after aging for 110 hr	

<b>FIGURE</b>	<b>PAGE</b>
and reaction temperature at 150°C for 15 hr. TPA/Si ratios, x, are: a) 0.05; b) 0.1; c) 0.2; d) 0.3; e) 0.4 and f) 0.5 mol ratio	28
4.11 Effect of dilution on product morphology formed after aging for 110 hr and heating at 150°C for 15 hr at the water ratio ,x, of: a) 114; b) 140; c) 170 mol ratio	29
4.12 IR spectrum of products formed from reaction of SiO <sub>2</sub> :xTiO <sub>2</sub> : 0.4NaOH:0.3TPA:114H <sub>2</sub> O with reaction conditions of 110 hr aging time, 150°C reaction temperature, 15 hr reaction time for a-b, 20 hr reaction time for c-e, 25 hr reaction time for f and 35 hr reaction time for g-h. Si/Ti ratios, x , are: a) 100.00; b) 33.33; c) 20.00; d) 14.29; e) 10.00; f) 7.69; g) 5.88 and h) 5.0	31
4.13 DR-UV pattern of products formed from reaction of SiO <sub>2</sub> :xTiO <sub>2</sub> : 0.4NaOH:0.3TPA:114H <sub>2</sub> O with reaction conditions of 110 hr aging time, 150°C reaction temperature, 15 hr reaction time for a-b, 20 hr reaction time for c-e, 25 hr reaction time for f and 35 hr reaction time for g-h. Si/Ti ratios, x , are: a) 100.00; b) 33.33; c) 20.00; d) 14.29; e) 10.00; f) 7.69; g) 5.88 and h) 5.0	32
4.14. Effect of Si/Ti on product morphology formed after aging for 110 hr and heating at 150°C for 15 hr reaction time for a-b, 20 hr reaction time for c-e, 25 hr reaction time for f and 35 reaction time for g-h. Si/Ti ratios, x , are: a) 100.00; b) 33.33; c) 20.00; d) 14.29; e) 10.00; f) 7.69; g) 5.88 and h) 5.0	33