

การเกิดโพลิเมอร์สหพันธ์แบบต่อของเอ็น, เอ็น-เมทิลีนบิส-
อะครีลามีดบนเส้นใยไหมด้วยแมงกานีส (III) อะซีทิลอะซีโทเนต



นางสาวสิริรัตน์ จารุจินดา

วิทยานิพนธ์นี้เป็นส่วนหนึ่งของการศึกษาตามหลักสูตรปริญญาวิทยาศาสตรมหาบัณฑิต

สาขาวิชาวิทยาศาสตร์โพลิเมอร์

บัณฑิตวิทยาลัย จุฬาลงกรณ์มหาวิทยาลัย

พ.ศ. 2534

ISBN 974-579-353-1

ลิขสิทธิ์ของบัณฑิตวิทยาลัย จุฬาลงกรณ์มหาวิทยาลัย

017897

๒๕๓๔

GRAFT COPOLYMERIZATION OF N,N'-METHYLENEBISACRYLAMIDE
ONTO SILK FIBRES BY MANGANESE (III) ACETYLACETONATE

Miss Sireratana Charruchinda

A Thesis Submitted in Partial Fulfillment of the Requirements
for the Degree of Master of Science

Program of Polymer Science

Graduate School

Chulalongkorn University

1991

ISBN 974-579-353-1

Copyright of the Graduate School, Chulalongkorn University

พิมพ์ที่ศูนย์พิมพ์หนังสือพิมพ์ไทยในกรุงเทพมหานคร

SIRERATANA CHARRUCHINDA : GRAFT COPOLYMERIZATION OF N,N'-MBA ONTO SILK FIBRES BY MANGANESE(III) ACETYLACETONATE. THESIS ADVISOR : ASSO. PROF.SUDA KIATKAMJORNWONG, Ph.D., ASST. PROF.WERASAK UDOMKICHDECHA, Ph.D., 131 pp., ISBN 974-579-353-1

The present research concerns the synthesis of graft copolymer of N,N'-MBA onto silk fibres by using manganese (III) acetylacetonate as initiator. Percentage grafting was investigated by varying $Mn(acac)_3$ concentrations within the range of 0.5×10^{-3} to 2.5×10^{-3} mole- l^{-1} and by varying the N,N'-MBA concentrations within the range of 2.5×10^{-3} to 15.0×10^{-3} mole- l^{-1} while the concentrations of NaLS and $HClO_4$ were kept constant at 2.0×10^{-3} mole- l^{-1} and at 7.5×10^{-3} mole- l^{-1} , respectively. The reaction required 2 hrs with temperature at $50^\circ C$.

Interestingly, percentage grafting increases with an increase in $Mn(acac)_3$ concentrations, whereas it is insignificantly related to an increase in N,N'-MBA concentrations. This is due to the bulky structure of N,N'-MBA by which the approach of N,N'-MBA to form charge transfer complex with $Mn(acac)_3$ is sterically hindered.

The structure of N,N'-MBA-grafted silk fibres was analyzed by an infrared spectroscopic method, and the physical properties were examined in relation to the percentage grafting on the basis of the result of textile strength, thermal analysis, dyeability with acid dyes and surface characteristics.

It is found that an increase in percentage grafting and percentage of homopolymer causes the reduction of tensile strength. In addition, the dyeability of the N,N'-MBA-grafted silk fibres was lower than that of the ungrafted silk fibres. The surface characteristics of N,N'-MBA-grafted silk fibres are uneven and rough, and the fibrils are separated from the silk fibres. However, when considering thermal decomposition temperature, the N,N'-MBA-grafted silk fibres show the inclination to the higher temperature.

ภาควิชา Petro - Polymer
สาขาวิชา Polymer Science
ปีการศึกษา 2533

ลายมือชื่อนิสิต Sireratana Charruchinda
ลายมือชื่ออาจารย์ที่ปรึกษา Suda Kiatkamjornwong
ลายมือชื่ออาจารย์ที่ปรึกษาช่วย Udomkichdecha



ฉวีรัตน์ จารุจินดา : การเกิดโพลีเมอร์สหพันธ์แบบต่อของ เอ็น,เอ็น-เมทิลีนบิสอะคริลามิดบนเส้นใยไหมด้วยแมงกานีส(III) อะซิทิลอะซิโทเนต (GRAFT COPOLYMERIZATION OF N,N'-METHYLENEBISACRYLAMIDE ONTO SILK FIBRES BY MANGANESE(III) ACETYLACETONATE) อ.ที่ปรึกษา : รศ. ดร.สดา เกียรติกำจรวงศ์, ผศ. ดร.วีระศักดิ์ อดุมกิจเดชา, 131 หน้า. ISBN 974-579-353-1

ในงานวิจัยนี้ได้สังเคราะห์โพลีเมอร์สหพันธ์แบบต่อของ เอ็น,เอ็น-เมทิลีนบิสอะคริลามิดบนเส้นใยไหมด้วยแมงกานีส(III) อะซิทิลอะซิโทเนตเป็นสารเริ่มต้นปฏิกิริยา ได้ทำการศึกษาดัชนีที่มีผลต่อร้อยละของการกราฟต์ โดยการศึกษาความเข้มข้นของเอ็น,เอ็น-เมทิลีนบิสอะคริลามิด ที่ความเข้มข้น $2.5 \times 10^{-3} - 15.0 \times 10^{-3}$ โมล-ลิตร⁻¹ ศึกษาความเข้มข้นของแมงกานีส(III) อะซิทิลอะซิโทเนตที่ความเข้มข้น $0.5 \times 10^{-3} - 2.5 \times 10^{-3}$ โมล-ลิตร⁻¹ โดยทำการสังเคราะห์ที่ความเข้มข้นของกรดเปอร์คลอริก 7.5×10^{-3} โมล-ลิตร⁻¹ ความเข้มข้นของโซเดียมลอริลซัลเฟต 2.0×10^{-3} โมล-ลิตร⁻¹ อุณหภูมิ 50^oซ. เป็นเวลา 2 ชม.

การศึกษพบว่า ร้อยละของการกราฟต์เพิ่มขึ้นเมื่อความเข้มข้นของสารเริ่มต้นปฏิกิริยาเพิ่มขึ้น ในขณะที่การเพิ่มความเข้มข้นของเอ็น,เอ็น-เมทิลีนบิสอะคริลามิดไม่ค่อยมีความสำคัญต่อการเพิ่มขึ้นของร้อยละของการกราฟต์ ทั้งนี้เนื่องมาจากโครงสร้างของเอ็น,เอ็น-เมทิลีนบิสอะคริลามิดขนาดใหญ่ ทำให้การเข้าไปทำปฏิกิริยาเกิด charge transfer complex ทำได้ยาก กราฟต์โพลิเมอร์ที่ได้ ถูกลำบากพิสูจน์เอกลักษณ์ ด้วยอินฟราเรดสเปกโตรสโคปี จากนั้นนำมาทดสอบสมบัติทางกายภาพต่าง ๆ ที่มีความสัมพันธ์กับการเกิดกราฟต์ อันได้แก่ ความคงทนต่อแรงดึง สมบัติในการย้อมติดสี ลักษณะพื้นผิว และความคงทนต่อความร้อน

จากการศึกษาพบว่า การเพิ่มร้อยละของการกราฟต์ และร้อยละของโพลิเมอร์เอกพันธ์ทำให้ค่าความคงทนต่อแรงดึงต่ำลง นอกจากนี้สมบัติในการย้อมติดสีแอซิดบนเส้นไหมที่ผ่านการกราฟต์แล้ว ยังต่ำกว่าเส้นไหมที่ไม่ได้ผ่านการกราฟต์ ลักษณะพื้นผิวที่ได้ไม่สม่ำเสมอ และมีขนของเส้นใยแยกออกมาจากเส้นใยไหมด้วย อย่างไรก็ตาม ความคงทนต่อความร้อนของเส้นใยไหมที่ผ่านการกราฟต์มีค่าสูงกว่าเส้นใยไหมที่ไม่ได้ผ่านการกราฟต์

ภาควิชา สหสาขาวิชาปิโตร-โพลิเมอร์
สาขาวิชา วิทยาศาสตร์โพลิเมอร์
ปีการศึกษา 2533

ลายมือชื่อนิสิต ส.อ.อ. สุร

ลายมือชื่ออาจารย์ที่ปรึกษา ผศ. วีระศักดิ์

.....



ACKNOWLEDGEMENTS

The author wishes to express her deeply sincere gratitude and appreciation to her advisor, Associate Professor Dr. Suda Kiatkamjornwong for her worthy advise on this thesis and also to her co-advisor, Assistant Professor Dr. Werasak Udomkichdecha.

She also wishes to thank the thesis committee: Associate Professor Dr. Pattarapan Prasassarakich, Dr. Nuntaya Yanumet and Assistant Professor Onusa Saravari. Especially, she wishes to thank Dr. Nuntaya Yanumet, Mrs. Ngarmchit Thawalyavichachit and her colleagues at the Textile Industry Division, and also her friends, for their assistance and encouragement.

In addition, the financial grant and support for the thesis work, provided by The Graduate School, Chulalongkorn University as well as the provision of instruments, chemicals and research facilities by the Department of Materials Science are gratefully acknowledged.

Last but not least, the author greatly appreciates her dear mother, father, brothers and sister for their love, inspiration and encouragement throughout her study.



CONTENTS

	PAGE
ABSTRACT (IN ENGLISH)	i
ABSTRACT (IN THAI)	ii
ACKNOWLEDGEMENTS	iii
CONTENTS	iv
LIST OF TABLES	xiii
LIST OF FIGURES	x
ABBREVIATION	xii
CHAPTER	
I INTRODUCTION	1
1.1 THE PURPOSE OF THE INVESTIGATION	1
1.2 OBJECTIVE	6
1.3 SCOPES OF INVESTIGATION	6
II THEORY AND LITERATURE SURVEY	8
2.1 SILK	8
2.2 N,N'-METHYLENEBISACRYLAMIDE	11
2.3 GRAFT COPOLYMERIZATION	12
2.3.1 Free-radical Graft Copolymerization	13
2.4 INITIATION	15
2.4.1 Redox Initiation	15
2.4.2 Thermal Decomposition and Mechanical Degradation	17

2.4.2	Ionizing Radiation	17
2.4.4	Ultraviolet Radiation	18
2.4.5	Chain Transfer and Copolymerization	18
2.5	METAL CHELATES	19
2.5.1	Manganese(III) Acetylacetonate	21
2.6	FACTORS INFLUENCING THE PERCENTAGE GRAFT COPOLYMERIZATION	24
2.6.1	Initiator	24
2.6.2	Monomer	26
2.6.3	Acidity	28
2.6.4	Temperature	28
2.6.5	Time	29
2.6.6	Additives	29
2.7	CHARACTERIZATION OF GRAFT COPOLYMER .	32
2.8	LITERATURE SURVEY	32
III	EXPERIMENTAL	39
3.1	CHEMICALS AND INSTRUMENTS	39
3.2	PREPARATION OF RAW MATERIALS FOR GRAFTING REACTION	42
3.2.1	Purification of Raw Silk Fibres	42
3.2.2	Purification and Recrystallization of N,N'-MBA	42

3.3	GRAFT COPOLYMERIZATION OF N,N'-MBA ONTO SILK FIBRES BY MANGANESE(III) ACETYLACETONATE	43
3.4	CHARACTERIZATION OF N,N'-MBA GRAFTED SILK FIBRES	46
3.4.1	Infrared Spectroscopy	46
3.5	DETERMINATION OF PHYSICAL PROPERTIES SIGNIFICANTLY RELEVANT TO GRAFT COPOLYMERIZATION OF N,N'-MBA ONTO SILK FIBRES	47
3.5.1	Tensile Strength and Elongation	47
3.5.2	Thermal Properties	47
3.5.3	Surface Characteristics	48
3.5.4	Dyeability Properties of the Grafted Silk Fibres	48
IV	RESULTS AND DISCUSSION	55
4.1	CHARACTERISTICS OF THE GRAFTED SILK FIBRES BY INFRARED SPECTROMETRY	55
4.2	EFFECT OF CONCENTRATION OF MANGANESE (III) ACETYLACETONATE ($Mn(acac)_3$) ON GRAFT YIELD	60
4.3	EFFECT OF N,N'-MBA CONCENTRATION ON GRAFT YIELD	71

4.4	EFFECT OF CONCENTRATION OF MANGANESE (III) ACETYLACETONATE ($Mn(acac)_3$) ON PERCENTAGE OF HOMOPOLYMER	73
4.5	EFFECT OF N,N'-MBA CONCENTRATION ON PERCENTAGE OF HOMOPOLYMER	76
4.6	TENSILE STRENGTH AND PERCENTAGE ELONGATION	82
4.7	THERMAL PROPERTY	88
4.8	DYEABILITY PROPERTY OF N,N'-MBA GRAFTED SILK FIBRES	91
4.8.1	Dyeability Property of N,N'-MBA Grafted Silk Fibres .	91
4.9	SURFACE CHARACTERISTICS	96
V	CONCLUSION AND SUGGESTION	99
	REFERENCES	103
	APPENDIX A	108
	APPENDIX B	110
	APPENDIX C	112
	APPENDIX D	116
	APPENDIX E	119
	VITA	131

LIST OF TABLES

TABLE		PAGE
1.1	Export of silk fabrics and silk products	3
1.2	Domestic consumption of silk fabrics and silk products	4
2.1	Amino acid compositions of fibroin	9
2.2	Structural formulae of the main amino acid contained in fibroin	10
2.3	Results of bulk polymerization of MMA initiated by $\text{Me}(\text{acac})_x$	23
3.1	Detail of materials used	39
3.2	Detail of chemicals used	40
3.3	Detail of instruments and equipment used	41
3.4	Formula used in the grafting reaction of $\text{N,N}'\text{-MBA}$ onto silk fibres	44
4.1	Effect of concentration of $\text{Mn}(\text{acac})_3$ and $\text{N,N}'\text{-MBA}$ on grafting of $\text{N,N}'\text{-MBA}$ onto silk fibres	61
4.2a	The correlation coefficient (r) between variables and properties	63
4.2b	Multiple regression between variables and properties	64
4.3	Effect of concentration of $\text{Mn}(\text{acac})_3$ and $\text{N,N}'\text{-MBA}$ on tensile strength and elongation of grafted silk fibres	83

4.4	The thermal properties of ungrafted and N,N'-MBA grafted silk fibres	90
4.5a	Dyeability property of N,N'-MBA-grafted silk fibres on Supranol Fast Orange GSN 140%	93
4.5b	Dyeability property of N,N'-MBA-grafted silk fibres on Kayacyl Sky Blue R	94
E.1	The concentration of stock solution of dyestuff and their λ_{\max} in 50% pyridine	121
E.2a	Calibration curve of Supranol Fast Orange GSN 140%	122
E.2b	Calibration curve of Kayacyl Sky Blue R	123
E.3	The percentage purity of dyestuffs	129

LIST OF FIGURES

FIGURE	PAGE
2.1 Polymerization of styrene using metal acetyl-acetonates as initiators	22
3.1 Schematic diagram of the dyeing and washing process	51
4.1a IR-spectrum of N,N'-MBA	56
4.1b IR-spectrum of ungrafted silk fibres	57
4.1c IR-spectrum of N,N'-MBA grafted silk fibres	57
4.2 Effect of Mn(acac) ₃ concentration on variation of % grafting	62
4.3 Effect of N,N'-MBA concentration on variation of % grafting	72
4.4 Effect of Mn(acac) ₃ concentration on variation of % homopolymer	74
4.5 Effect of N,N'-MBA concentration on variation of % homopolymer	77
4.6a Tensile strength of N,N'-MBA-grafted silk fibres in relation to % grafting [N,N'-MBA] = 2.5 x 10 ⁻³ mole-l ⁻¹	85
4.6b Tensile strength of N,N'-MBA-grafted silk fibres in relation to % grafting [N,N'-MBA] = 5.0 x 10 ⁻³ mole-l ⁻¹	86

4.6c	Tensile strength of N,N'-MBA-grafted silk fibres in relation to % grafting [N,N'-MBA] = 7.5×10^{-3} mole-l ⁻¹	86
4.6d	Tensile strength of N,N'-MBA-grafted silk fibres in relation to % grafting [N,N'-MBA] = 10.0×10^{-3} mole-l ⁻¹	87
4.6e	Tensile strength of N,N'-MBA-grafted silk fibres in relation to % grafting [N,N'-MBA] = 15.0×10^{-3} mole-l ⁻¹	87
4.7	Thermal properties of ungrafted and N,N'-MBA - grafted silk fibres	89
4.8a	Scanning electron micrograph of ungrafted silk fibres	97
4.8b	Scanning electron micrograph of N,N'-MBA-grafted silk fibres (4% grafting)	97
4.8c	Scanning electron micrograph of N,N'-MBA-grafted silk fibres (6% grafting)	98
4.8d	Scanning electron micrograph of N,N'-MBA-grafted silk fibres (7.5% grafting)	98
E.1a	Absorption spectrum of Supranol Fast Orange GSN 140% in 50% pyridine	120
E.1b	Absorption spectrum of Kayacyl Sky Blue R	120
E.2a	Calibration curve of Supranol Fast Orange GSN 140% in 50% pyridine at $\lambda_{\max} = 505 \text{ nm}$	124
E.2b	Calibration curve of Kayacyl Sky Blue R in 50% pyridine at $\lambda_{\max} = 640 \text{ nm}$	124

ABBREVIATION

N,N'-MBA	N,N'-methylenebisacrylamide
Mn(acac) ₃	Manganese(III) acetylacetonate
M-O	Metal-oxygen
MMA	Methyl methacrylate
I	Initiator
R [•]	Radical
~SH	Silk fibre
k _d	rate constant for initiator dissociation
k _i	rate constant for initiation
k _p	rate constant for propagation
k _t	rate constant for termination
Mn(facac) ₃	Manganese 1,1,1-trifluoroacetylacetonate
AN	Acrylonitrile
AA	Acrylic acid
MA	Methyl acrylate
BA	Butyl acrylate
PMMA	Polymethyl methacrylate
Me-OH	Methanol
EtOH	Ethanol
n-Pr-OH	n-propanol
n-butyl-OH	n-butanol
CHCl ₃	Chloroform
CCl ₄	Carbon tetrachloride

EtSH	mercaptan
HEMA	Hydroxy ethylmethacrylate
MAA	Methacrylamide
MAN	Methacrylonitrile
HClO ₄	Perchloric acid
owf	on weight of fibres
λ	wavelength
r	correlation coefficient
A	Absorbance
ν	stretching vibration
δ	bending vibration