

อิทธิพลของแสงอัลตราไวโอเลตที่มีต่อการเสื่อมสภาพของฟิล์มพอลิโอเลฟิน

นางสาว พรเพ็ญ อาทกรกิจวัฒน์



วิทยานิพนธ์นี้เป็นส่วนหนึ่งของการศึกษาตามหลักสูตรปริญญาวิทยาศาสตรมหาบัณฑิต

ภาควิชาวิทยาศาสตร์

บัณฑิตวิทยาลัย จุฬาลงกรณ์มหาวิทยาลัย

ปีการศึกษา 2539

ISBN 974-634-989-9

ลิขสิทธิ์ของบัณฑิตวิทยาลัย จุฬาลงกรณ์มหาวิทยาลัย

I 17420131

**INFLUENCE OF ULTRAVIOLET LIGHT ON DEGRADATION
OF POLYOLEFIN FILMS**

MISS PORNPEN ATORNGITJAWAT

สถาบันวิทยบริการ

A Thesis submitted in Partial Fulfillment of the Requirements
for the Degree of Master of Science

Department of Material Science

Graduate School

Chulalongkorn University

Academic Year 1996

ISBN 974-634-989-9

Thesis Title Influence of Ultraviolet Light on Degradation of
Polyolefin Films.
By Miss Pornpen Atorngitjawat
Department Materials Science
Thesis Advisor Associate Professor Werasak Udomkichdecha, Ph. D.
Thesis Co-Advisor Associate Professor Saowaroj Chuayjuljit

Accepted by the Graduate School, Chulalongkorn University in Partial
Fulfillment of the Requirements for the Master's Degree.

Santi Thoongsuwan
.....Dean of Graduate School

(Associate Professor Santi Thoongsuwan, Ph.D)

Thesis Committe

Paiparn Santisuk
.....Chairman
(Assistant Professor Paiparn Santisuk)

Werasak Udomkichdecha
.....Thesis Advisor
(Associate Professor Werasak Udomkichdecha, Ph.D)

S. Chuayjuljit
.....Thesis Co-Advisor
(Associate Professor Saowaroj Chuayjuljit)

Khemchai Hemachandra
.....Member
(Assistant Professor Khemchai Hemachandra, Ph.D)



พิมพ์ต้นฉบับบทความวิจัยวิทยานิพนธ์ภายในกรอบสี่เหลี่ยมนี้เพียงแผ่นเดียว

พระเพทญ์ อาทกรกิจวัฒน์ : อิทธิพลของแสงอัลตราไวโอเล็ตที่มีต่อฟิล์มพอลิโอเลฟิน (INFLUENCE OF ULTRAVIOLET LIGHT ON DEGRADATION OF POLYOLEFIN FILMS)

อ.ที่ปรึกษา : รศ. ดร. วีระศักดิ์ อุคมกิจเดชา 132 หน้า. ISBN 974-634-989-9

แผ่นฟิล์มพอลิโอเลฟิน 3 ชนิด คือ ฟิล์มพอลิโพรพิลีน ฟิล์มพอลิเอทิลีนชนิดความหนาแน่นสูง และ ฟิล์มพอลิเอทิลีนชนิดความหนาแน่นต่ำ ได้ถูกนำมาทดลองใน 2 ภาวะเปรียบเทียบกัน คือในภาวะธรรมชาติโดยตากแดดไว้กลางแจ้ง และในภาวะเร่งโดยใช้เครื่องซินเทสด์เบตาแลมปี ซึ่งควบคุมภาวะต่างๆ ให้คล้ายในภาวะธรรมชาติ จากนั้นจะศึกษาการแตกตัวของโครงสร้างทางเคมีจากหมู่คาร์บอนิลที่เกิดขึ้น (ค่าคาร์บอนิลอินเดกซ์) และหาความสัมพันธ์ระหว่างค่าคาร์บอนิลอินเดกซ์กับเวลาที่ได้รับแสงของฟิล์มทั้ง 2 ภาวะ ในเชิงคณิตศาสตร์

ผลการวิจัยพบว่า การเพิ่มขึ้นของค่าคาร์บอนิลอินเดกซ์มีความสัมพันธ์แบบเอกซ์โพเนนเชียลกับการเพิ่มขึ้นของเวลาที่ได้รับแสง และมีความสัมพันธ์กับสมบัติเชิงกลที่เสียไป คือการยืดตัว ณ จุดขาดจะลดลงเมื่อค่าคาร์บอนิลอินเดกซ์เพิ่มขึ้น ขณะที่ค่ามอดูลัสจะแสดงผลในทางตรงกันข้าม และความเปราะของฟิล์มจะเป็นตัวบ่งชี้เวลาที่ทำให้ฟิล์มเกิดการเสื่อมสภาพเนื่องจากแสง ซึ่งพบว่าในภาวะธรรมชาติฟิล์มพอลิโพรพิลีน ฟิล์มพอลิเอทิลีนชนิดความหนาแน่นสูง และฟิล์มพอลิเอทิลีนชนิดความหนาแน่นต่ำจะเสื่อมสภาพในเวลา 9 23 และ 24 สัปดาห์ตามลำดับ ขณะที่ในภาวะเร่งฟิล์มทั้งสามชนิดจะเสื่อมสภาพในเวลา 114 684 และ 912 ชั่วโมงตามลำดับ

สถาบันวิทยบริการ
จุฬาลงกรณ์มหาวิทยาลัย

ภาควิชา วิศวกรรมศาสตร์
สาขาวิชา วิทยาศาสตร์พอลิเมอร์และเทคโนโลยี
สีทอง
ปีการศึกษา 2539

ลายมือชื่อนิสิต พทศ.น. อาทกรกิจวัฒน์
ลายมือชื่ออาจารย์ที่ปรึกษา *Wit Uthairat*
ลายมือชื่ออาจารย์ที่ปรึกษาพร้อม *S. Chuayjuljit*

** C726290 : MAJOR APPLIED POLYMER SCIENCE AND TEXTILE TECHNOLOGY

KEY WORD: PHOTODEGRADATION / DEGRADATION / WEATHERING / POLYOLEFINS

PORNPEN ATORNGITJAWAT : INFLUENCE OF ULTRAVIOLET LIGHT ON DEGRADATION OF POLYOLEFIN FILMS. THESIS ADVISOR :

ASSO. PROF. WERASAK UDOMKICHDECHA, Ph.D. 132 pp. ISBN 974-634-989-9

Three different commercial grade polyolefin films : polypropylene (PP), high density polyethylene (HDPE), and low density polyethylene (LDPE) have been studied. Two methods were carried out simultaneously for comparison between outdoor exposure and simulated condition in Xenotest Beta Lamp machine. The amount of carbonyl group formation (carbonyl index), was used as a key indicator to represent the chemical structure break-down. Mathematical models to express the relationship between exposure time and carbonyl index were proposed in both conditions.

It was found that the carbonyl index increased exponentially as the exposure time increased. On the other hand, mechanical properties in terms of elongation at break decreased and hence increasing in initial modulus. Mechanical properties lost indicates the photooxidative degradation time of the films which became brittle. For outdoor exposure condition, it was also observed that the degradation times for PP, HDPE and LDPE were 9, 23 and 24 weeks respectively, while those for accelerated test were 114, 684 and 912 hours respectively.

สถาบันวิทยบริการ

จุฬาลงกรณ์มหาวิทยาลัย

ภาควิชา..... วัสดุศาสตร์

สาขาวิชา..... วิทยาศาสตร์พอลิเมอร์และเทคโนโลยี
[เคมีสิ่งทอ]

ปีการศึกษา..... 253๘

ลายมือชื่อนิสิต..... พมพันธ์ อุทรากิจวัฒน์

ลายมือชื่ออาจารย์ที่ปรึกษา..... Uth Uth

ลายมือชื่ออาจารย์ที่ปรึกษาร่วม..... S. Chuayjuljit

ACKNOWLEDGEMENT

I would like to express my gratitude to my advisor Associate Professor Dr. Werasak Udomkichdecha and co-advisor Associate Professor Saowaroj Chuayjuljit for their encouraging guidance, supervision and helpful suggestion throughout this study. In addition, I am also grateful to Assistant Professor Dr. Khemchai Hemachandra and Assistant Professor Paiparn Santisuk for their assistance and comments during this work.

A special thank is extended to the Department of Materials Science and the staff for the in valuable assistance.

This study was supported by grants from the National Science and Technology Development Agency, Ministry of Environment and by raw materials from Thai Polyethylene Co., Ltd.; these supports are gratefully acknowledged.

Furthermore, many thanks to my friends and all those who encourage me over the years of my study.

Finally, I would like to express my love and gratitude to my family for their love, encouragement and supporting.

CONTENTS

	Page
Abstract (Thai).....	iv
Abstract (English).....	v
Acknowledgement	vi
Contents	vii
List of Tables	x
List of Figures	xii
Chapter	
1. Introduction.....	1
2. Literature survey	3
2.1 Polyolefin films.....	6
2.1.1 Low Density Polyethylene.....	7
2.1.2 High Density Polyethylene	9
2.1.3 Polypropylene	12
2.2 Photo-oxidation of polymer	14
2.2.1 Photo-oxidation of polyolefins	16
2.3 Factors comprising weather	20

Contents (continue)

	Page
2.3.1 Radiation.....	21
2.3.2 Temperature.....	22
2.3.3 Oxygen.....	23
2.3.4 Water.....	23
2.4 Tensile properties of polymer.....	24
2.5 Chemical properties.....	27
2.6 Fourier transform infrared spectroscopy.....	28
3. Experimental Procedure.....	29
3.1 Raw Materials.....	29
3.2 Exposure Conditions.....	31
3.2.1 Outdoor exposure.....	33
3.2.2 Accelerated UV exposures.....	34
3.3 Analytical Methods.....	36
3.3.1 Infrared absorption.....	36
3.3.2 Tensile testing.....	37
4. Results and Discussions.....	40
4.1 Polypropylene (PP).....	40
4.1.1 Changes in chemical structures.....	40

Contents (continue)


	Page
4.1.2 Changes in the mechanical properties	46
4.2 High Density Polyethylene (HDPE)	49
4.2.1 Changes in chemical structures	49
4.2.2 Changes in the mechanical properties	52
4.3 Low Density Polyethylene	55
4.3.1 Changes in chemical structures	55
4.3.2 Changes in the mechanical properties	59
4.4 The comparative results among the three polyolefin films	62
5. Conclusion	65
References	67
Appendices	70
A Wastestrem and plastic in packaging	71
B Raw data of chemical properties	74
C Raw data of mechanical properties	80
Curriculum vitae	132

LIST OF TABLES

Table	Page
2.1 Energy of radiation of different wavelengths and bond energy of typical bonds found in polymers.....	22
3.1 Physical properties of polyolefin films	29
3.2 Data of Thailand weathering climate.....	30
4.1 Carbonyl index of PP films at each exposure time in outdoor exposure and in Xenotest	45
4.2 Influence of carbonyl index on mechanical properties of PP films	47
4.3 Carbonyl index of HDPE films at each exposure time in outdoor exposure and in xenotest	51
4.4 Influence of carbonyl index on mechanical properties of HDPE films	53
4.5 Carbonyl index of LDPE films at each exposure time in outdoor exposure and in xenotest	58
4.6 Influence of carbonyl index on mechanical properties of LDPE films.....	60

Table (continue)

Table	Page
4.7 Exponential models represent changes in carbonyl index with increasing in exposure time in both conditions	63



สถาบันวิทยบริการ
จุฬาลงกรณ์มหาวิทยาลัย

LIST OF FIGURES

Figure	Page
2.1 Oxidation and photooxidation scheme.....	16
2.2 Photochemical reaction of polyolefins.....	19
2.3 Photochemical reaction of polyethylene.....	19
2.4 Photochemical reaction of polypropylene.....	20
3.1 Average radiation exposure at Bangkok Metropolis during 1986-1994.....	31
3.2 The average of UV and total radiation exposure at Bangkok Metropolis during 1986-1994.....	31
3.3 The average temperature and relative humidity at Bangkok Metropolis during 1986-1994.....	32
3.4 Average rainfall at Bangkok Metropolis during 1986-1994.....	32
3.5 The exposure racks using for outdoor exposure.....	33
3.6 The Xenotest Beta Lamp machine for accelerated UV exposure.....	35
3.7 FTIR spectrometer model impact 400D	37

Figure (continue)

Figure	Page
3.8 The LR 100K Lloyd Universal Testing machine.....	39
4.1 IR spectrum of carbonyl groups of PP films in both exposures	41
4.2 Carbonyl index variation with exposure time for PP films	45
4.3 Elongation at break values in relationship to carbonyl index of PP films	48
4.4 Initial modulus in relationship to carbonyl index of PP films	48
4.5 IR spectrum of carbonyl groups of HDPE films in both exposures	50
4.6 Carbonyl index variation with exposure time for HDPE films	51
4.7 Elongation at break values in relationship to carbonyl index of HDPE films	54
4.8 Initial modulus in relationship to carbonyl index of HDPE films	54
4.9 IR spectrum of carbonyl groups of LDPE films in both exposures	57
4.10 Carbonyl index variation with exposure time for LDPE films ...	58

Figure (continue)

Figure	Page
4.11 Elongation at break values in relationship to carbonyl index of LDPE films.....	61
4.12 Initial modulus in relationship to carbonyl index of LDPE films.....	61
4.13 Changes of values in elongation at break versus carbonyl index of the three examined films in both conditions.....	64
4.14 Changes of values in initial modulus versus carbonyl index of the three examined films in both conditions.....	64

สถาบันวิทยบริการ
จุฬาลงกรณ์มหาวิทยาลัย