

การผลิตยางบุรีต้านระดับขยายส่วน



นาย พงศธร ฤทธิ์

วิทยานิพนธ์นี้ เป็นส่วนหนึ่งของการศึกษาตามหลักสูตรปรัชญาวิทยาศาสตร์มหาบัณฑิต

ภาควิชาเคมี เทคโนโลยี

ปัจจุบันวิทยาลัย จุฬาลงกรณ์มหาวิทยาลัย

พ.ศ. 2537

ISBN 974-583-912-4

ลิขสิทธิ์ของปัจจุบันวิทยาลัย จุฬาลงกรณ์มหาวิทยาลัย

LARGE SCALE PRODUCTION OF DEPROTEINIZED RUBBER



Mr. Pongsatorn Koosakul

A Thesis Submitted in Partial Fulfillment of the Requirements

for the Degree of Master of Science

Department of Chemical Technology

Graduate School

Chulalongkorn University

1994

ISBN 974-583-912-4

Thesis Title Large scale production of deproteinized rubber

By Mr. Pongsatorn Koosakul

Department Chemical Technology

Thesis Advisor Mr. Pienpak Tasakorn, Ph.D.

Associate Professor Jariya Boonjawat, Ph.D.



Accepted by the Graduate School, Chulalongkorn University in
Partial Fulfillment of the Requirements for the Master's Degree/

Thavorn Vajrabhaya Dean of Graduate School
(Professor Thavorn Vajrabhaya, Ph.D.)

Thesis Committee

K. Bunyakait Chairman
(Associate Professor Kunchana Bunyakait, M.Sc.)

P. Tasakorn Thesis Advisor
(Mr. Pienpak Tasakorn, Ph.D.)

Jariya Boonjawat Thesis Coadvisor
(Associate Professor Jariya Boonjawat, Ph.D.)

Shooshat Barame Member
(Associate Professor Shooshat Barame, Ph.D.)

C425617 : MAJOR CHEMICAL TECHNOLOGY

KEY WORD: DEPROTEINIZED RUBBER / NATURAL RUBBER / MIXING

PONGSATORN KOOSAKUL : LARGE SCALE PRODUCTION OF DEPROTEINIZED RUBBER.

THESIS ADVISOR : MR. PIENPAK TASAKORN, Ph.D. THESIS CO-ADVISOR :

ASSO. PROF. JARIYA BOONJAWAT, Ph.D. 107 pp. ISBN 974-583-912-4

Constant-viscosity deproteinized rubber (CV-DPNR) is produced by removal of protein from latex and viscosity stabilized by the addition of 0.15 p.h.r. hydroxylamine hydrochloride. CV-DPNR has more consistent Mooney viscosity and less water absorption resulting in improvement in dynamic properties. This makes CV-DPNR suitable for engineering and medical applications.

The purpose of this study was to develop the purification method of natural rubber by removal of proteins and to produce CV-DPNR from field latex of 4 clones, RRIM 600, PB 28/59, PB 5/51 and GT 1. It was found that, by using papain at 0.3 p.h.r. in a 50 litre agitated tank, at 50°C and at turbulence intensity factor of 50-55, the reduction of nitrogen content was maximum, being 82-90 % depending on rubber clones, within 50 minutes under steam coagulation. Apart from nitrogen content, papain treatment also improved raw rubber properties such as ash content, dirt content, volatile matter, Mooney viscosity, storage hardening and color index. It did not impose any effect the molecular weight distribution.

Comparative study on the cure characteristics between CV-rubber and CV-DPNR showed that deproteinization resulted in increasing scorch time and decreasing cure rate. After vulcanization, the physical properties of CV-DPNR were compared with its control CV-non-deproteinized rubber. The results showed that vulcanized CV-DPNR had an increase in tensile strength, tear strength, elongation at break, whereas hardness and 300 % modulus were lower than its control.

ศูนย์วิทยทรพยากร
จุฬาลงกรณ์มหาวิทยาลัย

ภาควิชา เคมีเทคนิค

ลายมือชื่อนิสิต ท.ส. ๙๕

สาขาวิชา เคมีเทคนิค

ลายมือชื่ออาจารย์ที่ปรึกษา ดร. สมชาย ใจดี

ปีการศึกษา ๒๕๓๖

ลายมือชื่ออาจารย์ที่ปรึกษาร่วม ดร. ยุทธนา ใจดี



พิมพ์ต้นฉบับที่ดัดย่อวิทยานิพนธ์ภายในกรอบสีเขียวนี้เพียงแผ่นเดียว

พงศธร คุสกุล : การผลิตยางไปร์เด็นดำในระดับขยายส่วน (LARGE SCALE PRODUCTION OF DEPROTEINIZED RUBBER) อ.ที่ปรึกษา : ดร.เพียรพรค ทัศคร. อ.ที่ปรึกษาร่วม : รศ.ดร.จริยา บุญญวัฒน์ 107 หน้า ISBN 974-583-912-4

ยางไปร์เด็นดำที่มีค่าความหนืดคงที่ (CV-DPNR) คือยางที่ได้สกัดไปร์เด็นออก และทำให้มีความหนืดคงที่โดยเดินสาร hydroxylamine hydrochloride ยางไปร์เด็นดำที่มีค่าความหนืดคงที่นี้จะดูดซับน้ำหน่อย ทำให้สมบูรณ์ทางเคมีศาสตร์ดีขึ้น จึงเหมาะสมกับการนำไปใช้งานทางด้านวิศวกรรมและทางการแพทย์

วัตถุประสงค์ของงานวิจัยนี้ คือ การหาวิธีการที่เหมาะสมในการสกัดไปร์เด็นออกจากยางพารา และผลิตยางไปร์เด็นดำที่มีค่าความหนืดคงที่จากน้ำยางสด 4 พันธุ์ คือ RRIM 600, PB 28/59, PB 5/51 และพันธุ์ GT 1 ชี้งพบว่า วิธีการที่เหมาะสม คือ ใช้เอนไซม์ป่าเป็น 0.3 p.h.r. ในถังกว้างขนาด 50 ลิตร ที่อุณหภูมิ 50° ช ぐวนที่ค่าดัชนีความชื้นปวนในการกรองในช่วง 50-55 และใช้ไอน้ำในการทำให้ยางจับตัว จะสามารถลดไข่ในโครงร่าง ในยางได้ประมาณ 82-90 % บีบพันธุ์ยาง โดยใช้เวลา 50 นาที นอกจากนี้ยางที่ลดไปร์เด็นลงยังมีค่า เถ้า พง ความชื้น ความหนืดคงที่ ดัชนีสี ดำ และไม่มีผลกระแทกต่อการกระจายตัวของน้ำหนักไม่เกิดข้อผิดพลาดของยาง

จากการศึกษาลักษณะการสกัดของยาง พบร่วมกับยางไปร์เด็นดำที่มีค่าความหนืดคงที่จะเพิ่มเวลา ยางเริ่มคงรูป และมีอัตราการสกัดมากกว่ายางที่ไม่สกัดไปร์เด็นที่ค่าความหนืดคงที่ ในด้านสมบูรณ์ทางวัสดุค่าในช่องยางไปร์เด็นดำที่มีค่าความหนืดคงที่ มีค่าแรงดึงยางขนาด แรงฉีก และเบอร์ เทียนการยืดตัวสูง แต่ความแข็ง และโมดูลัสที่ 300 % ลดลงเมื่อเปรียบเทียบกับยางที่ไม่ได้สกัดไปร์เด็นที่มีค่าความหนืดคงที่

ศูนย์วิทยบริการ วุฒิการณ์มหาวิทยาลัย

ภาควิชาเคมีเทคนิค
สาขาวิชาเคมีเทคนิค
ปีการศึกษา2536

ลายมือชื่อนิสิต
ลายมือชื่ออาจารย์ที่ปรึกษา
ลายมือชื่ออาจารย์ที่ปรึกษาร่วม



ACKNOWLEDGEMENT

I wish to express my deepest gratitude and appreciation to Dr. Pienpak Tasakorn, my advisor and Assoc. Prof. Dr. Jariya Boonjawat, my co-advisor for their encouragements, suggestions, discussions, supports and helpful guidance throughout this research. I would like to acknowledge my thesis committee, Assoc. Prof. Kunchana Bunyakait, and the members of my thesis committee, Assoc. Prof. Shooshat Barame, for their suggestions, advice and encouragements.

I would like to thank National Science and Technology Development Agency (NSTDA) for financial supports through project; "Development of Technically Specified Natural Rubber for Industrial and Engineering Applications" (Principal Investigator : Jariya Boonjawat). Special thanks are due to all staff members of Banpan Research Laboratory Co., Ltd. for their helps and providing equipments in vulcanizate properties testing. Special thanks are due to Bangkok Rubber Co., Ltd. and Rayong Bangkok Rubber Co., Ltd. for their supply of the rubber and rubber materials. Special thanks are due to Miss Vipa Savetanit and all staff members of the Rubber Research Institute of Bangkok for providing equipments for raw rubber testing. Special thanks are due to Department of Biochemistry for providing the facilities in laboratory, some chemicals and equipments.

Finally, I wish to express my deepest thanks to my family, all teachers and friends in the Department of Chemical Technology and Biochemistry who always give me encouragement, warmest love, understanding, knowledge and friendship.



CONTENTS

	PAGE
ABSTRACT (IN ENGLISH)	i
ABSTRACT (IN THAI)	ii
ACKNOWLEDGEMENT	iii
LIST OF TABLES	vi
LIST OF FIGURES	vii
ABBREVIATION	ix
CHAPTER I INTRODUCTION	1
1.1 Introduction	1
1.2 Raw rubber production	2
1.3 Objectives	5
CHAPTER II Literature reviews and theoretical considerations	6
2.1 Natural rubber (Para rubber)	6
2.2 Solid natural rubber	12
2.3 Deproteinized natural rubber	14
2.4 Theoretical considerations	21
CHAPTER III METERIALS AND EXPERIMENTAL METHOD	29
3.1 Materials	29
3.2 Apparatus	30
3.3 Experimental method	33
3.4 CV-DPNR production	36
3.5 Testing of the properties of DPNR	36
CHAPTER IV RESULTS	38
4.1 The stabilizing effect of Triton X-100	38
4.2 Effect of temperature on deproteinization	39
4.3 Effect of agitation speed on deproteinization .	41

	PAGE
4.4 Effect of papain concentration on deproteinization	44
4.5 Effect of deproteinization on the molecular weight distribution.....	44
4.6 Properties of CV-DPNR	48
CHAPTER V DISCUSSION	61
5.1 The condition for deproteinization	61
5.2 Effect of deproteinization on MWD	64
5.3 The properties of CV-DPNR	65
5.4 Estimated cost of production of CV-DPNR	69
CHAPTER VI CONCLUSIONS	71
REFERENCES	73
APPENDIX	79
VITA	108



 ศูนย์วิทยบรังษยการ
 จุฬาลงกรณ์มหาวิทยาลัย

LIST OF TABLES

TABLE	PAGE
1.1 The major rubber producers in the world, 1981-1992	3
2.1 Composition of latex	7
2.2 Average molecular weight, molecular weight distribution of some clonal rubber	9
2.3 Development in manufacture of low nitrogen rubber	19
2.4 Specifications of DPNR	20
4.1 The stabilizing effect of Triton X-100 concentration on deproteinization	39
4.2 Weight average molecular weight and molecular weight distribution of CV-DPNR, its control and commercial rubber grades	47
5.1 Production cost of CV-DPNR	70
A.2.1 The compound formulation chosed for assessing the cure behavior of natural rubber	95

LIST OF FIGURES

FIGURE	PAGE
1.1 Production and exports of rubber in Thailand, 1981-1992 ..	3
2.1 The chemical structure of <u>Hevea</u> rubber	8
2.2 Types of molecular weight distribution curve of natural rubber	10
2.3 Arrhenius plot	24
2.4 Rubber particle	27
2.5 Effect of θ on deproteinization	28
3.1 A reactor set for deproteinization of rubber latex	32
3.2 Scheme of CV-DPNR production	34
4.1 Effect of temperature on deproteinization	40
4.2 Effect of time on deproteinization using a reactor of 11 cm diameter at 57 rpm impeller speed	42
4.3 Effect of various agitation speed on deproteinization using a reactor of 41 cm diameter	43
4.4 Effect of papain concentration on deproteinization	45
4.5 The comparative study of MWD	46
4.6 Comperison of raw rubber properties	49
4.7 Comperison of raw rubber color	50
4.8 Comparison of the physical properties of raw rubber	52
4.9 Mooney viscosity before and after storage	53
4.10 Comperison of cure characteristics	55
4.11 Comperison of compound rubber color	56
4.12 Comperison of vulcanized properties	57

FIGURE	PAGE
4.13 Comperison of vulcanized rubber color	59
5.1 Effect of temperature on nitrogen reduction	62
5.2 Effect of intensity factor on deproteinization	63
A.1.1 Repeat the experiment on the effect of agitation speed	
at 50 rpm	83
A.1.2 Repeat the experiment on the effect of agitation speed	
at 60 rpm	83
A.1.3 Repeat the experiment on the effect of papain concentration	
at 0.25 p.h.r.	84
A.1.3 Repeat the experiment on the effect of papain concentration	
at 0.3 p.h.r.	84
A.2.1 The molecular weight calibration curve of polystyrene	
standard	93
A.2.2 Rheometer curing curve	97
A.2.3 Shape of dumb-bell test pieces	99
A.2.4 Shape of test piece for tear strength test	100
A.4.1 ln k vs 1/T	106

ABBREVIATION

A	Weight of crucible plus ash
B	Weight of empty crucible
C	Weight of test sample before drying
CV-NR	Constant viscosity natural rubber
CV-DPNR	Constant viscosity deproteinized natural rubber
D	Weight of test sample after drying
DRC	Dry rubber content
E	Enzyme
E _a	Activity energy
GPC	Gel permeation chromatography
k	Rate constant
k ₀	frequency factor
L	Impeller diameter, cm
M	Molarity of the H ₂ SO ₄
Mn	Number average molecular weight
Mw	Weight average molecular weight
MWD	Molecular weight distribution
N	Impeller speed, rev/s
P	Power input as in page 26
P ₀	Initial plasticity value of the unaged test
P _H	Plasticity value after storage hardening test
Δ P	The accelerated storage hardening
p	Probability that the substrate must contract with the active site

p.h.r.	Part per hundred of dry rubber
PRI	Plasticity Retention Index
Re	Impeller Reynolds number, $Re = \rho NL^2 / \mu$
S	Substrate
THF	Tetrahydrofuran
V	Volume of a drop; liquid contents in a vessel, m^3
V_1	Volume of H_2SO_4 for titrate of the content, cm^3
V_2	Volume of H_2SO_4 for titrate of the blank, cm^3
W	Weight of rubber taken
Z	Constant normalizing to unit time and unit volume
Å°	Angstrom
$^\circ C$	Degree Celcius
K	Degree Kelvin
e	Energy dissipated per unit mass
\bar{e}	Average energy dissipated per unit mass
μm	Micrometre
μ	The viscosity of latex, $g cm^{-1} sec^{-1}$
ρ	The density of the latex, g/cm^3
θ	Turbulence intensity factor