

การศึกษาสารประกอบเชิงชอนของเหล็กจากสารละลายกรดเกลือ  
โดยการสกัดคั่วตัวทำละลาย



นางสาวปริยา วิริyanนท์

001694

วิทยานิพนธ์นี้เป็นส่วนหนึ่งของการศึกษาตามหลักสูตรปริญญาวิทยาศาสตรมหาบัณฑิต<sup>บัญชี</sup>  
แผนกวิชาเคมี

บัณฑิตวิทยาลัย จุฬาลงกรณมหาวิทยาลัย

พ.ศ. ๒๕๑๖

๑๖๕๒๙๘๑

A STUDY OF IRON(III) CHLORIDE COMPLEX FROM HYDROCHLORIC  
ACID SOLUTION BY SOLVENT EXTRACTION

Miss Preeya Viriyanon



A Thesis Submitted in Partial Fulfillment of the Requirements  
for the Degree of Master of Science

Department of Chemistry

Graduate School

Chulalongkorn University

1973

Accepted by Graduate School, Chulalongkorn University  
in partial fulfillment of the requirements for Degree of  
Master of Science

B. Tamthai

.....  
Dean of the Graduate School

Thesis Committee

Nara Boon-Loy ..... Chairman

Maeu Amarasit .....

Suehat Mongkolphantha .....

Thesis Supervisor :

Dr. Salag Dhabhanandha

Date : .....

27<sup>th</sup> May, 1976

หัวข้อวิทยานิพนธ์ การสักดิสารประกอบเชิงชั้นของเหล็ก จากสารละลายน้ำกรเกลือ  
โดยการสักดิคุยตัวทำละลาย

ชื่อ นางสาว ปริญญา วิริยานันท์

แผนกวิชา เคมี

ปีการศึกษา 2515

### บทคัดย่อ

จุดประสงค์ของการทดลอง เพื่อศึกษาสารประกอบเชิงชั้นของเหล็ก ที่มีออกซิเดชันนัมเบอร์สาม ซึ่งมีคลอไรด์เป็นตัวล้อมรอบ ( ligand ) ในตัวทำละลายประเทอสเทอโร พวกละซิเตตตัวที่ใช้สักดิคือ n-amyl acetate,  $\beta$ -methyl butyl acetate, n-butyl acetate และ n-propyl acetate จากการที่ใช้ absorption spectra ที่ได้จากการวัด absorbance ในช่วง ultraviolet ของสารประกอบเชิงชั้นของเหล็กนั้น แสดงให้เห็นว่าสารตั้งกล่าวใน  $\lambda_{max}$  ที่ 362, 312 และ 255 nm. ยกเว้นกรณีที่ใช้  $\beta$ -methyl butyl acetate ซึ่งปรากฏว่าไม่แสดง absorbance ที่  $\lambda_{max}$  225 nm absorbance ที่  $\lambda_{max}$  ส่องอันแรกถือโดยทั่วไปว่า เป็นลักษณะประจำตัวของอนุพล  $FeCl_4^-$  จากผลการทดลองมีหลักฐานนี้ยืนยันว่า สารประกอบเชิงชั้นของเหล็กที่มีออกซิเดชันนัมเบอร์สาม ซึ่งสักดิได้จากการกรเกลือคือ  $HFeCl_4$  ซึ่งเมื่อถูกสักดิด้วย n-amyl acetate พบรูมูล์ไม่เด่นชัดของเอสเทอโร่เก่าที่คงอยู่บุก ๆ หนึ่งไม่เด่นชัดของ  $HFeCl_4$  คาดว่าเป็นสาเหตุที่ไม่สามารถติดต่ำการเปลี่ยนแปลงความสามารถในการสักดิเหล็กเมื่อเปลี่ยนความเข้มข้นของเอสเทอโร่และได้ศึกษาพบว่าสัมประสิทธิ์ของการสักดิเหล็กที่มีออกซิเดชันนัมเบอร์สาม เพิ่มขึ้นตามความเข้มข้นของกรเกลือ และได้ค่ามากที่สุดเมื่อใช้กรเกลือเข้มข้น 7-8 โนล่า คือ ให้ค่าสัมประสิทธิ์ 2 ของ การสักดิ 6.7  $\times 10^2$  และ 1.1  $\times 10^3$  เมื่อใช้ n-amyl acetate และ  $\beta$ -methyl butyl acetate ทั้งหมดกับ

จากการศึกษา phase diagram พนว่า เมื่อเปรียบเทียบระบบ 3 ระบบ คือ ระบบหมุนแท่นหักบัวท้าวทำละลายอินทรี ระบบหมุนนำ ท้าวทำละลายอินทรี และกรดเกลือที่ความเข้มข้นต่าง ๆ กัน กับระบบหมุนนำ ท้าวทำละลายอินทรี กรดเกลือและเกลือเพอร์วิคคลอไรความเข้มข้นต่าง ๆ ขนาดของการละลายของนำและท้าวทำละลายอินทรีในระบบหมุน แตกต่างจากระบบท่อสูงและสาม ตัวระบบท่อสูงและสามกล้ายคลึงกัน ถ้าจะต้องว่า สาเหตุของความแตกต่างกังวลเรื่องมากนักมีการเปลี่ยนแปลงคุณภาพของท้าวทำละลายเพราการเติมกรดและเกลือของเหลวลงไป ระบบหมุนนำมารายงานในวิทยานิพนธ์นี้ ถือว่าเป็นระบบประเภท "non ideal"

Thesis Title : A Study of Iron(III)Chloride Complex from  
Hydrochloric Acid Solution by Solvent Extraction

Name : Miss Preeya Viriyanon

Department : Chemistry

Academic Year : 1972

#### ABSTRACT

The iron(III)chloro complexes in the ester extracts i.e., n-amyl acetate,  $\beta$ -methyl butyl acetate, n-butyl acetate, and n-propyl acetate were studied by the spectrophotometric method. The ultra-violet absorption spectra show the absorption peaks at 362, 312, and 255 nm, the third peak was disappeared in the  $\beta$ -methyl butyl acetate extract. The first two peaks are generally taken as the characteristic of the tetrachloroferrate ion( $\text{FeCl}_4^-$ ). The most probable solvation number of four for the  $\text{HFeCl}_4^-$  species in the n-amyl acetate was found by the dilution technique. The distribution coefficient of iron(III) in hydrochloric acid-amyl acetate systems was studied radiometrically. The distribution coefficient increases with increasing hydrochloric acid concentration until the maximal values of  $6.7 \times 10^2$  and  $1.1 \times 10^3$  were reached using n-amyl acetate and  $\beta$ -methyl butyl acetate respectively at 7.8 M-hydrochloric acid.

The conditions for the non-ideality of the system were studied along with other studies. The major piece of informations comes from the study of the phase diagrams of 3 components i.e., water-hydrochloric acid-n-amyl acetate and water-hydrochloric acid solution of ferric chloride-n-amyl acetate. The changes in the solvent properties were shown by the mutual solubility of aqueous and non-aqueous solutions affected by the addition of hydrochloric acid in the phase diagram and this was claimed to be one of other criteria set by previous workers for non-ideality of the system.

## ACKNOWLEDGEMENTS

The author wishes to express her deep gratitude to Dr.Salag Dhabhanandha for her guidance, and patient assistance both with experimental work and in the preparation of the thesis.

She wishes to thank Dr.Vichai Posyachinda for the donation of the high specific activity iron-59.

She is indebted to Prince of Songkla University for granting leave for study and to the Department of Chemistry of Chulalongkorn University for arranging a University Development Commission Scholarship for carrying out her experimental work.

Finally, she wishes to acknowledge the help of her friends who gave assistance with experiments and in drawing of figures.

## CONTENTS

|   | PAGE |
|---|------|
| ABSTRACT (in Thai).....   | iv   |
| ABSTRACT .....  | vi   |
| ACKNOWLEDGEMENTS .....  | viii |
| CHAPTER   |      |
| I. INTRODUCTION .....   | 1    |
| II. PRELIMINARY WORK .....  | 6    |
| 2.1 The Distribution Coefficient of Iron(III)<br>in Various Organic Solvents .....                  | 8    |
| 2.2 The Empirical Formula of the Iron(III)<br>Chloro Complexes in the Organic Phases ...            | 9    |
| 2.3 Spectrophotometric Studies of Iron(III)<br>Chloro Complexes .....                               | 10   |
| 2.4 The Significance of Water in the<br>Extraction .....  | 11   |
| 2.5 The Solvation Number of the Extracted<br>Iron(III)Chloro Complexes in Organic<br>Solvents ..... | 12   |
| III. EXPERIMENTAL PROCEDURE .....   | 14   |
| 3.1 Reagents .....  | 14   |
| 3.2 Procedure .....   | 18   |

## PAGE

|  |    |
|--|----|
| IV. RESULTS .....  | 27 |
| Lists of tables.....   | 27 |
| Lists of figures.....  | 35 |
| V. DISCUSSION AND CONCLUSION.....  | 44 |
| 5.1 Spectrophotometric Studies of Iron(III)<br>Chloro Complexes.....                       | 44 |
| 5.2 The Distribution Coefficient of Iron(III)<br>in Hydrochloric Acid-Amyl Acetate Systems | 48 |
| 5.3 The Solvation Number of HFeCl <sub>4</sub> in n-Amyl<br>Acetate.....                   | 49 |
| 5.4 Concluding Remarks and Suggestions for<br>Future Work .....                            | 52 |
| REFERENCES .....   | 58 |
| BIOGRAPHY .....  | 61 |