

CHAPTER V

CONCLUSION

For this new in-situ regeneration, called SECR for this study, vapor phase application can be effective to regenerate spent activated carbon. As the amount of rinsing water is increased, the effective capacity of the regenerated activated carbon is not improved. The remaining SDS on the carbon surface after regeneration may result in a significant reduction in its adsorption capacity.