

**THE EFFECT OF DOPANTS ON THE RESISTIVITY OF
CONDUCTIVE POLYMER-COATED FABRIC**

Ms. Tidarat Wongpun

A Thesis Submitted in Partial Fulfilment of the Requirements
for the Degree of Master of Science
The Petroleum and Petrochemical College, Chulalongkorn University
in Academic Partnership with
Case Western Reserve University, The University of Michigan,
The University of Oklahoma, and Institut Français du Pétrole

2004

ISBN 974-9651-68-5

I 21619074

Thesis Title: The Effect of Dopants on the Resistivity of Conductive
Polymer-Coated Fabric
By: Ms. Tidarat Wongpun
Program: Polymer Science
Thesis Advisors: Assoc. Prof. Nantaya Yanumet
Prof. Edgar A. O'Rear, III

Accepted by the Petroleum and Petrochemical College, Chulalongkorn
University, in partial fulfilment of the requirements for the Degree of Master of
Science.

K. Bunyakiat.
..... College Director
(Assoc. Prof. Kunchana Bunyakiat)

Thesis Committee:

Nantaya Yanumet.
.....
(Assoc. Prof. Nantaya Yanumet)

Edgar A. O'Rear
.....
(Prof. Edgar A. O'Rear, III)

R. Magaraphan
.....
(Asst. Prof. Rathanawan Magaraphan)

M. Nithitanakul
.....
(Dr. Manit Nithitanakul)

ABSTRACT

4572024063: POLYMER SCIENCE PROGRAM

Tidarat Wonpun: The effect of dopants on the resistivity of
conductive polymer-coated fabric

Thesis Advisors: Assoc. Prof. Nantaya Yanumet and
Prof. Edgar A. O'Rear, III, 73 pp. ISBN 974-9651-68-5

KEYWORD: Conductive fabric/ Polyaniline/ Polythiophene/
Sulfonic acid/ Dopant

Polyaniline and polythiophene were coated on polyester fabric by using admicellar polymerization technique. The effects of dopant type including, benzene sulfonic acid (BSA), p-toluenesulfonic acid (PTSA), (+)-camphor-10-sulfonic acid (β) (CSA), and 5-sulfosalicylic acid (5-SCA) and of dopant concentration were studied. Two methods of doping were investigated. The results showed that the apparent surface and volume resistivity of the doped fabric decreased with increasing dopant concentration over the range 1-10 mM for polyaniline and over the range 10-60 mM for polythiophene, respectively. Doping during the first step was found to be an effective method for polyaniline. For polythiophene, doping after the final step of admicellar polymerization was effective for PTSA and 5-SCA, while doping during the first step was suitable for CSA. For polyaniline-coated fabric, the values of resistivity obtained from the fabric doped with BSA, PTSA and CSA did not differ much and the lowest resistivity obtained was around 10^8 ohm. For polythiophene, the lowest resistivity obtained was with 5-SCA followed by PTSA and CSA, with the lowest resistivity around 10^9 ohm. SEM micrographs of the treated fabrics showed a thin film of the polymer deposited on the fiber surface.

บทคัดย่อ

ธิดารัตน์ วงษ์พันธุ์: ผลของตัวเติมที่มีต่อความต้านทานไฟฟ้าของผ้าพอลิเอสเตอร์ที่เคลือบด้วยพอลิเมอร์นำไฟฟ้า (The Effect of Dopants on the Resistivity of Conductive Polymer-Coated Fabric) อาจารย์ที่ปรึกษา: ร ศ.ดร. นันทยา ขานูเมศ และ ศ.ดร. เอ็ดการ์ โอเรียร์ 73 หน้า ISBN 974-9651-68-5

พอลิแอนนิลีนและพอลิไทโอฟีนถูกเคลือบบนผ้าโดยวิธีแอ็ดไมเซลลาพอลิเมโรเซชัน โดยได้มีการศึกษาผลของชนิดของตัวเติมและความเข้มข้นของตัวเติมที่มีต่อค่าความต้านทานไฟฟ้าของผ้า ตัวเติมที่ใช้ประกอบด้วย เบนซีนซันโฟนิกแอซิด (บีเอสเอ), พาราโทลูอินซัลโฟนิกแอซิด (พีทีเอสเอ), (+)-แคมฟอร์เทนซัลโฟนิกแอซิด (ซีเอสเอ) และ ไฟว์ซัลโฟซาลลิไซลิกแอซิด (5-เอสซีเอ) นอกจากนี้ยังได้มีการศึกษาการเติมในสองวิธี ผลจากการศึกษาพบว่าค่าความต้านทานไฟฟ้าเชิงพื้นผิวและเชิงปริมาตรของผ้าที่ผ่านการเติมมีค่าลดลงเมื่อความเข้มข้นของตัวเติมเพิ่มขึ้นในช่วง 1-10 มิลลิโมลาร์ สำหรับพอลิแอนนิลีน และ 10-60 มิลลิโมลาร์ สำหรับพอลิไทโอฟีน ตามลำดับ วิธีเติมระหว่างชั้นตอนแรกของแอ็ดไมเซลลาพอลิเมโรเซชันมีประสิทธิภาพสำหรับพอลิแอนนิลีน ในส่วนของพอลิไทโอฟีน การเติมระหว่างชั้นตอนแรกดีสำหรับตัวซีเอสเอ ในขณะที่วิธีการเติมหลังชั้นตอนสุดท้ายเหมาะสำหรับตัวพีทีเอสเอและ 5-เอสซีเอ สำหรับผ้าที่เคลือบด้วยพอลิแอนนิลีน ค่าความต้านทานไฟฟ้าที่ได้จากการเติมด้วย บีเอสเอ พีทีเอสเอ และ ซีเอสเอ ต่างกันเพียงเล็กน้อย โดยค่าความต้านทานไฟฟ้าต่ำสุดที่ได้อยู่ในช่วง 10^3 โอห์ม ในขณะที่ผ้าที่เคลือบด้วยพอลิไทโอฟีน ค่าต่ำสุดที่ได้อยู่ในช่วง 10^4 โอห์ม โดยได้จากการเติมด้วย 5-เอสซีเอ ตามด้วย พีทีเอสเอ และซีเอสเอ ภาพของผิวเส้นใยที่ผ่านการเคลือบซึ่งถูกวิเคราะห์ด้วยกล้องจุลทรรศน์อิเล็กตรอนแบบส่องกราดพบว่ามีฟิล์มบางของพอลิเมอร์เคลือบอยู่บนผิวเส้นใย

ACKNOWLEDGEMENTS

With a deep sense of gratitude, I wish to express my sincere thanks to both of my advisors, Prof. Edgar A O'Rear for his kindness and suggestion, and Assoc. Prof. Nantaya Yanumet, for her immense help in planning and executing the work in time, she not only spent countless hours in work discussion and provided immediate comments, but was also most supportive for any proposed ideas with great encouragement throughout this research.

I extend my appreciation to the members of my thesis committee, Asst. Prof. Rattanawan Makaraphan and Dr. Manit Nithitanakul, not only for their guidance in writing this thesis, but also for their advice, concern, and encouragement during my study and research.

I am grateful to my parents, who taught me the value of hard work by their own examples. I would like to share this moment of happiness with my mother and brothers. They rendered me enormous support during the whole tenure of my research. The encouragement and motivation that were given to me to carry out my research work by my father is also remembered.

My colleagues at the Petroleum and Petrochemical College, Chulalongkorn University, all gave me the feeling of being at home at work. I am thankful for having them as my colleagues.

This thesis work is partially funded by Postgraduate Education and Research Programs in Petroleum and Petrochemical Technology (PPT Consortium).

Finally, I would like to thank all whose direct and indirect support helped me in completing my thesis in time.

TABLE OF CONTENTS

	PAGE
Title Page	i
Abstract (in English)	iii
Abstract (in Thai)	iv
Acknowledgements	v
Table of Contents	vi
List of Tables	ix
List of Figures	x
CHAPTER	
I INTRODUCTION	1
II LITERATURE REVIEW	3
2.1 Admicellar Polymerization	3
2.2 Thin Film Coating by Admicellar Polymerization	5
2.3 Preparing Conductive Fabric	8
2.4 Concept of Doping	13
2.5 Volume and Surface Measurement of Fabric	17
III EXPERIMENTAL	20
3.1 Materials	20
3.1.1 Monomer	20
3.1.2 Oxidizing Agent	20
3.1.3 Surfactant	20
3.1.4 Dopant	20
3.1.5 Fabric	20

CHAPTER	PAGE
3.2 Equipment	21
3.3 Experimental Procedures	21
3.3.1 Purification of Conductive Monomer	21
3.3.2 Admicellar Polymerization	21
3.3.3 Doping of the Coated Fabric	22
3.3.4 Testing and Characterization	23
IV THE EFFECT OF DOPANTS ON THE RESISTIVITY OF POLYANILINE-COATED POLYESTER FABRIC BY ADMICELLAR POLYMERIZATION	24
Abstract	24
Introduction	25
Experimental	26
Results and Discussion	28
Conclusions	31
Acknowledgements	31
References	32
V THE EFFECT OF DOPANTS ON THE RESISTIVITY OF POLYTHIOPHENE-COATED POLYESTER FABRIC BY ADMICELLAR POLYMERIZATION	40
Abstract	40
Introduction	41
Experimental	42
Results and Discussion	44
Conclusions	47
Acknowledgements	47
References	48

CHAPTER	PAGE
VI CONCLUSIONS AND RECOMMENDATIONS	56
REFERENCES	58
APPENDICES	61
Appendix A Resistivity of Polyaniline Coated Fabric	61
Appendix B Resistivity of Polythiophene Coated Fabric	63
Appendix C All data Resistivity of Polyaniline Coated Fabric	65
Appendix D All data Resistivity of Polythiophene Coated Fabric	68
Appendix E Resistivity of untreated and undoped fabric	71
CURRICULUM VITAE	73

LIST OF TABLES

TABLE		PAGE
CHAPTER II		
2.1	The structures of all dopants used in the present study	18
CHAPTER III		
3.1	Admicellar polymerization conditions.	22

LIST OF FIGURES

FIGURE	PAGE
CHAPTER II	
2.1	The admicellar polymerization process 3
2.2	Typical adsorption isotherm of surfactants on a solid surface 4
2.3	Protonic acid doping and oxidative doping of polyaniline 14
2.4	Different redox forms of PTH: (a) reduced, (b) half-oxidized (polaronic), and (c) oxidized (bipolaronic) 16
CHAPTER IV	
1	Steps in admicellar polymerization process 35
2	Comparison of the surface and volume resistivity upon doping in conjunction with the first step of admicellar polymerization and upon doping subsequent to deposition of a film by admicellar polymerization 36
3	Effect of dopant type and dopant concentration on the resistivity 37
4	Comparison of the surface and volume resistivity of doped polyaniline using 10 mM of dopant 38
5	SEM micrographs of (a) untreated and (b) undoped polyaniline coated polyester fabric (c) doped fabric using 10 mM of PTSA 39
CHAPTER V	
1	Steps in admicellar polymerization process 51
2	Comparison of the surface and volume resistivity upon doping in conjunction with the first step of AP and upon doping subsequent to deposition of a film by AP 52
3	Effect of dopant type and dopant concentration on the resistivity 53
4	Comparison of the surface and volume resistivity of doped polythiophene using 20 mM of dopant. 54

FIGURE	PAGE
5. SEM micrographs of (a) untreated polyester fabric (b) undoped polythiophene coated polyester fabric and (c) doped fabric using 20 mM of PTSA.	55